

# 301 STAINLESS STEEL

PRODUCT DATA BULLETIN



**Aircraft Structural Parts**

**Cooking Utensils**

**Roof Drainage**

**Automotive Trim**

**Subway Cars**

## Applications Potential

Type 301 is an austenitic chromium-nickel stainless steel. This alloy is non-magnetic in the annealed condition, but becomes magnetic when cold worked. Within the scope of the ASTM Type 301 specification, chemical composition and processing modifications can result in a wide range of engineered material properties targeted at specific applications. Type 301 is available in the annealed as well as a variety of temper-rolled conditions.

High strength and excellent corrosion resistance make Type 301 Stainless Steel useful for a wide variety of applications. Typical uses include aircraft structural parts, trailer bodies, diaphragms, utensils, architectural and automotive trim, automobile wheel covers, roof drainage products, tableware, storm door frames, conveyor belts, sinks, subway cars and appliances.

## TABLE OF CONTENTS

Product Description .....	1
Composition .....	1
Available Forms .....	1
Mechanical Properties .....	2
Physical Properties .....	4
Weldability .....	5
Specifications .....	5



## PRODUCT DESCRIPTION

Type 301 is an austenitic chromium-nickel stainless steel that provides high strength and good ductility when cold worked. It is a modification of Type 304 in which the chromium and nickel contents are lowered to increase the cold work-hardening range. This permits higher tensile strengths to be achieved by rolling with a lower loss of ductility than with Type 304.

The grade is essentially non-magnetic when annealed. However, when the grade is cold worked, it becomes more magnetic than other standard austenitic stainless steels.

<b>COMPOSITION</b>		<b>(wt %)</b>
Carbon	(C)	0.15 max.
Manganese	(Mn)	2.00 max.
Phosphorus	(P)	0.045 max.
Sulfur	(S)	0.030 max.
Silicon	(Si)	0.75 max.
Chromium	(Cr)	16.00 – 18.00
Nickel	(Ni)	6.00 – 8.00
Nitrogen	(N)	0.10 max.
Iron	(Fe)	Balance

### AVAILABLE FORMS

AK Steel produces Type 301 Stainless Steel in thicknesses from 0.01 – 0.187 in. (0.25 – 4.75 mm) max. and widths up to 60 in. (1524 mm). For other thicknesses and widths, please contact your AK Steel sales representative.



## MECHANICAL PROPERTIES

**TABLE 1 – TYPICAL ROOM TEMPERATURE MECHANICAL PROPERTIES**

Condition	UTS ksi. (MPa)	0.2% YS ksi. (MPa)	Elongation % in 2" (50.8 mm)	Rockwell Hardness
Annealed	120 (827)	45 (310)	60	B86

**TABLE 2 – COLD-WORKED PROPERTIES**

Condition	UTS ksi. (MPa) min.*	0.2% YS ksi. (MPa) min.*	Elongation % in 2" (50.8 mm)		Rockwell Hardness
			< 0.015 in.	≥ 0.015 in.	
1/4 hard	125 (862)	75 (517)	25	25	C25
1/2 hard	150 (1034)	110 (758)	18	18	C32
3/4 hard	175 (1207)	135 (931)	12	12	C37
Full hard	185 (1276)	140 (965)	9	9	C41

\*Minimum - standard practice is to produce to either minimum tensile strength, minimum yield strength or minimum hardness, but not to combinations of these properties.

**TABLE 3 – FULL-HARD SHEET ELEVATED TEMPERATURE MECHANICAL PROPERTIES**

Temperature °F (°C)	UTS ksi. (MPa)	0.2% YS ksi. (MPa)	Elongation % in 2" (50.8 mm)
Room	185 (1276)	151 (1041)	9.0
200 (93)	174 (1200)	145 (1000)	7.0
400 (204)	168 (1158)	140 (965)	4.5
600 (316)	156 (1076)	130 (896)	6.0
800 (427)	145 (1000)	119 (820)	6.0

**TABLE 4 – LOW TEMPERATURE MECHANICAL PROPERTIES**



Condition	Temperature °F (°C)	UTS ksi. (MPa)	0.2% YS ksi. (MPa)	Elongation % in 2" (50.8 mm)
Annealed	-320 (-196)	275 (1896)	75 (517)	30
	-80 (-62)	195 (1344)	50 (345)	40
	-40 (-40)	180 (1241)	48 (331)	42
	32 (0)	155 (1069)	43 (296)	53
	70 (21)	110 (758)	40 (276)	60
Half-Hard	-320 (-196)	290 (1999)	115 (793)	25
	-80 (-62)	205 (1413)	105 (724)	37
	-40 (-40)	188 (1296)	101 (696)	38
	32 (0)	170 (1172)	98 (676)	46
	70 (21)	150 (1034)	110 (758)	48

## MECHANICAL PROPERTIES

**TABLE 5 – IMPACT ENERGY**

Test Temperature °F (°C)	Izod V-Notch ft.-lbs. (J)
-320 (-196)	114 (155)
-80 (-62)	112 (151)
-40 (-40)	110 (149)
32 (0)	108 (146)
70 (21)	102 (138)

**FIGURE 1 – EFFECT OF COLD WORK ON TENSILE PROPERTIES**



## PHYSICAL PROPERTIES

### PHYSICAL PROPERTIES

Density, lbs./in. <sup>3</sup> (g/cm <sup>3</sup> )	0.285 (7.88)
Electrical Resistivity, μΩ·in. (μΩ·cm) 68 °F (28.4 °C)	27.4 (69.5)
Thermal Conductivity, BTU/hr./ft./°F (W/m/K) 212 °F (100 °C) 932 °F (500 °C)	9.4 (16.2) 12.4 (21.4)
Coefficient of Thermal Expansion, in./in./°F (μm/m/K) 32 - 212 °F (0 - 100 °C) 32 - 600 °F (0 - 315 °C) 32 - 1000 °F (0 - 538 °C) 32 - 1200 °F (0 - 649 °C)	9.4 x 10 <sup>-6</sup> (16.9) 9.9 x 10 <sup>-6</sup> (17.8) 10.2 x 10 <sup>-6</sup> (18.4) 10.5 x 10 <sup>-6</sup> (18.7)
Modulus of Elasticity, ksi. (MPa) in tension in torsion	28.0 x 10 <sup>3</sup> (193 x 10 <sup>3</sup> ) 11.2 x 10 <sup>3</sup> (178 x 10 <sup>3</sup> )
Magnetic Permeability Annealed, (H/m at 200 Oersteds)	1.02 max.
Specific Heat, BTU/lbs./°F (kJ/kg/K) 32 - 212 °F (0 - 100 °C)	0.12 (0.50)
Melting Range, °F (°C)	2250 - 2590 (1399 - 1421)

### CORROSION RESISTANCE

Type 301 Stainless Steel exhibits corrosion resistance comparable to Types 302 and 304 in most mild service conditions. Resistance to food service requirements and atmospheric corrosion is excellent. Stress cracking resistance is similar to Type 304. The optimal corrosion resistance is obtained in the cold worked then annealed condition. When Type 301 is heated or cooled slowly through a temperature range of 800 - 1600 °F (427 - 871 °C) without subsequent annealing, it may undergo carbide precipitation that may result in intergranular corrosion.

### OXIDATION RESISTANCE

The maximum temperature to which Type 301 can be exposed continuously without appreciable scaling is about 1600 °F (871 °C). For intermittent exposure, the maximum exposure temperature is about 1450 °F (788 °C).

### HEAT TREATMENTS

Type 301 is non-hardenable by heat treatment.  
Annealing: Heat to 1900 - 2050 °F (1038 - 1121 °C), then water quench.  
Stress Relief Annealing: Heat to 500 - 900 °F (260 - 482 °C), then air cool.

### COLD WORKING

High hardness and strength for structural applications are achieved through cold working. In addition to the annealed condition 110 ksi. (758 MPa) minimum tensile strength, Type 301 strip is normally produced in various cold-rolled tempers up to full hard 185 ksi. (1276 MPa) minimum tensile strength.

### FORMABILITY

Type 301 can be readily formed and drawn. Due to its high work-hardening rate, intermediate annealing may be necessary for severe drawing and forming operations. Type 301 may not be suitable in certain severe forming applications where multiple forming operations are required.

### WELDABILITY

The austenitic class of stainless steels is generally considered to be weldable by the common fusion and resistance techniques. Special consideration is required to avoid weld "hot cracking" by assuring formation of ferrite in the weld deposit. This particular alloy is generally considered to have similar weldability than the most common alloy of this stainless class, Type 304L Stainless Steel. A major difference is the high C content for this alloy, which can cause the weld heat-affected-zones to be susceptible to intergranular corrosion in certain environments. When a weld filler is needed, AWS E/ER 308 is most often specified. Type 301 Stainless Steel is well known in reference literature and more information can be obtained in the following ways:

1. ANSI/AWS A5.9, A5.22 and A5.4 (filler metals, minimum UTS and elongation).
2. "Welding of Stainless Steels and Other Joining Methods," SSINA, (800:982-0355).
3. ANSI/AWS B2.1.009:2002 (GTAW 300's @ 0.50 in. - 0.14 in.).
4. ANSI/AWS B2.1-8-024:2001 (GTAW 300's @ 0.125 in. - 1.5 in.).
5. ANSI/AWS B2.1-8-013:2002 (SMAW 300's @ 0.050 in. - 0.14 in.).
6. ANSI/AWS B2.1-8-025:2001 (SMAW 300's @ 0.125 in. - 1.5 in.).
7. ANSI/AWS B2.1-8-005:2002 (GMAW 300's @ 0.050 in. - 0.14 in.).

### SPECIFICATIONS

Type 301 Stainless Steel is covered by the following specifications:  
**ASTM A240**  
**ASTM A666**



AK Steel Corporation  
9227 Centre Pointe Drive  
West Chester, OH 45069  
844.STEEL99 | 844.783.3599  
[www.aksteel.com](http://www.aksteel.com)  
[sales@aksteel.com](mailto:sales@aksteel.com)

AK Steel is a leading producer of flat-rolled carbon, stainless and electrical steel products, and carbon and stainless tubular products, primarily for automotive, infrastructure and manufacturing, construction and electrical power generation and distribution markets. Headquartered in West Chester, Ohio (Greater Cincinnati), the company employs approximately 8,500 men and women at eight steel plants, two coke plants and two tube manufacturing plants across six states (Indiana, Kentucky, Michigan, Ohio, Pennsylvania and West Virginia) and one tube plant in Mexico. Additional information about AK Steel is available at [www.aksteel.com](http://www.aksteel.com).

The information and data in this document are accurate to the best of our knowledge and belief, but are intended for general information only. Applications suggested for the materials are described only to help readers make their own evaluations and decisions, and are neither guarantees nor to be construed as express or implied warranties of suitability for these or other applications.

Data referring to material properties are the result of tests performed on specimens obtained from specific locations of the products in accordance with prescribed sampling procedures; any warranty thereof is limited to the values obtained at such locations and by such procedures. There is no warranty with respect to values of the materials at other locations.

AK and the AK Steel logo are registered trademarks of the AK Steel Corporation.

12.13.16

